

# **Technical Data Sheet**

Revision date: 2011.02.07

### 1. Product description

F is two-component raw material system on polyether base. The system is recommended to air filters gasket in machine manufacturing.

Two-component system	F – Component A	F - Component B
State of aggregation	liquid	liquid
Colour	dependent on pigment	brown
Smell	specific	specific
Viscosity at 25°C [mPas]	1000 - 1300	100 - 300
Density at 20°C [g/cm <sup>3</sup> ]	$1,03 \pm 0,03$	$1,21 \pm 0,03$

# 2. Application method recommended

Component A should be thoroughly mixed before use. Component B can be solid substance below  $10^{\circ}$ C. This component should be heated in original containers at temperature of  $60 - 70^{\circ}$ C to complete liquefying before processing. Liquefying time is usually 4 - 6 hours in the case of  $50 \text{ dm}^3$  containers and 18 - 24 hours in the case of  $216 \text{ dm}^3$  barrel. Because repeated heating can have negative influence on produced plastic properties, the whole of liquefied system processing is recommended. Moulding surfaces should be covered with suitable release agent to enable the profile easy taking out of the mould.

### 3. Technological properties of foaming process (cup test, 100g of the system)\*

Components A:B ratio Raw materials temperature	[g] [°C]	74,1 : 25,6 20
Start time	[s]	40 - 48
Gel time	İsi	75 – 95
End of rise	[s]	140 – 180
Free rise density	[kg/m³]	280 - 300

Optimum foam core density in the product	[kg/m³]	300 - 350
Hardness	[°ShA]	18 - 23

#### 5. Transport and storage

Store in dry, well ventilated room, in tightly closed containers. Protect against moisture access and direct exposure to sunrays. Containers opened before should be tightly closed and stored in position making out-flow impossible. Optimum storage temperature is  $15 - 30^{\circ}$ C. Permissible temperature during transport is  $5^{\circ}$ C  $- 50^{\circ}$ C.

### \*Notes

Data presented in this information have been obtained during the system foaming in model conditions. The results obtained when foaming in other conditions can be slightly different from published. Safety Data Sheet is available for the product. Every time the user is obliged to check the product and auxiliary agents usefulness for his intentional use.